



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-CN

Product Information

Careguard-CN is a new generation water and oil repelling fluorocarbon based on C6 Chemistry. It imparts durable water and oil repelling effects on various substrates viz., polyester, cotton, nylon, wool fibres and their blends without affecting the original hand of fabric. It can be applied by padding foam and by spray technique.

Key Features & Benefits

Key Features

Durable

No Roller build-up

Feel

Non ionic

Ecofriendly

Benefits

Good water/oil repellency after multiple home laundering

Suitable for high speed finishing operations

Does not affect the fabric hand

- No tailing during pad application
- Compatible with various softeners

PFOA below detectable limit

General Characteristics

Physical appearance : Off white to creamish liquid

Ionic nature : Nonionic

pH of 1% solution : 6 +/- 1

Miscibility : Miscible with water

Compatibility : Compatible with anionic, cationic and nonionic products

Stability : Stable to dilute acids and dilute alkalies

Application

Pick-up : 65-70%

Bath pH : 4.0 - 4.5

Drying : 100 - 120 deg.C

Curing : 150 deg.C,5 min. OR 160 deg.C,3 min. OR



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-CN

170 deg.C, 1 min.

SUGGESTED RECIPES:

For all substrates

Careguard-CN	:	20-80	g/l
Acetic Acid	:	0.5	g/l
IPA	:	5	g/l

* Concentration of Careguard-CN to be taken on the basis of durability requirement.

* For extended durability, addition of Crosslink-SC(Conc) is recommended

Note:

-
1. It is recommended to prewash the substrate to be treated with 1 g/l Saragen-DAM at 80-85 deg.C for 20-30 min. to remove traces of residual impurities to get excellent results.
 2. After padding and drying if fabric is kept overnight before curing, results will be further improved.
 3. Compatible with Flame Retardent finish (Pre-trial is recommended).
 4. Water-oil repellent finish can be combined with resin finish using 30g/l Saralink-ULF + 6g/l MgCl₂ + 20g/l Saralube-2975.

Sequence of addition:

-
- Prepare bath with all ingredients including Saralink-ULF, MgCl₂ in water containing Acetic acid.
 - Stir continuously and add Careguard-CN as the final ingredient.

Precautions:

-
- Avoid high speed and continuous stirring.



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-CN

- Avoid silicone based softeners in the finishing recipe.
- Pre trial with Careguard-CN is recommended with coating chemicals.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 8 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PC558 | Last Upd. On : 21/02/18] [PP]

This is a computer generated report. Hence not signed.