



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone: +91 22 42184218

Fax : +91 22 42184350

Email : tcmtkg@sarex.com

URL : www.sarex.com

PRODUCT LITERATURE

ECOFLUID-23

Product Information

Ecofluid-23 is a high viscosity diamino polydimethyl siloxane fluid. Ecofluid-23 is considered to be an ideal softening agent for cotton, woven/knits and its blends. Ecofluid-23 emulsion imparts soft, drapable and elastic handle on treated substrates. It improves the crease recovery angle, sewability, tear strength, abrasion resistance and wash and wear properties of treated substrates. The effects are reasonably durable to washing and dry cleaning.

Key Features & Benefits

Key Features

Durable

Multi-functional

Benefits

Reasonably durable to washing and dry cleaning

Imparts softness and also improves sewability and tear strength and reduces abrasion loss

General Characteristics

Physical appearance : Colourless to pale yellow, clear/hazy viscous liquid

Specific Gravity at 25 deg.C : 0.98 +/- 0.02

Refractive index : 1.403-1.409

Application

Padding Process:

Dosage : 15-20 g/l (30% emulsion)

Pick-up : 65-70 %

Bath pH : 5.0

Drying & Curing : 180 deg.C, 30-45 sec

Exhaust Process in winch or garment machine:

Dosage : 1.5-2% (30% emulsion)

Bath pH : 5.0

Bath Temp : 20-40 deg.C, 20-30 mins.



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone: +91 22 42184218

Fax: +91 22 42184350

Email: tcmtkg@sarex.com

URL: www.sarex.com

PRODUCT LITERATURE

ECOFLUID-23

Drying : Hydro extract

Instructions For Dilution

Emulsification:

It can be easily emulsified into stable micro emulsion by medium to high shear force mixer.

Typical formulation for micro-emulsion

	Weight parts

Ecofluid-23	18.0
* TDA 6 mole	7.0
* TDA 9 mole	5.0
Water-1	15.0
Water-2	20.0
Acetic acid	0.3-0.4
Water-3	35.0
Butyl di-glycol	1-2 (co-surfactant, if necessary)

* TDA: Tridecyl alcohol ethoxylate

Method:

-
- Take Ecofluid-23 & surfactants in a SS vessel and stir for 20-25 mins.
 - Add water-1 gradually under constant stirring and stir for 30 mins.
 - Add water-2 and stir for 20 mins.
 - Add water-3 and acetic acid; mix and stir for further 10-15 mins.
 - Add 1-2% co-surfactant if necessary.
 - Testing

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone: +91 22 42184218

Fax : +91 22 42184350

Email : tcmtkg@sarex.com

URL : www.sarex.com

PRODUCT LITERATURE

ECOFLUID-23

should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 8 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PE226 | Last Upd. On : 25/06/15] [MOLL]

This is a computer generated report. Hence not signed.