



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone: +91 22 42184218

Fax : +91 22 42184350

Email : tcmtkg@sarex.com

URL : www.sarex.com

PRODUCT LITERATURE

ECOFLUID - 8417

Product Information

Ecofluid-8417 is a low viscosity diamino functional silicone fluid. Ecofluid-8417 imparts exceptional softness on the treated substrates with good surface feel. It imparts durable softeners, crease resistance, elasticity for all types of fibers. Ecofluid-8417 also improves physical properties of fabrics.

Key Features & Benefits

Key Features

Non yellowing/No shade change

Multi-functional

Benefits

Can be applied on whites and dyed substrates

Imparts softness, crease resistance, elasticity and lubricity

General Characteristics

Physical appearance : Colourless fluid
Specific Gravity at 25 deg.C : 0.98 +/- 0.02
Refractive index : 1.405 - 1.410

Application

Padding Process:

Dosage : 15-20 g/l (30% emulsion)
Pick-up : 65-70%
Bath pH : 5.0-6.0
Drying : 130-160 deg.C

Exhaust Process in winch or garment machine:

Dosage : 1.5-2% (30% emulsion)
Bath pH : 5.0-6.0
Bath Temp. : 30-40 deg.C
Time : 20-30 mins.



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone: +91 22 42184218

Fax: +91 22 42184350

Email: tcmtkg@sarex.com

URL: www.sarex.com

PRODUCT LITERATURE

ECOFLUID - 8417

Instructions For Dilution

Emulsification:

It can be easily emulsified into stable micro emulsion by medium to high shear force mixer.

Typical formulation for micro-emulsion

	Weight parts

Ecofluid-8417	17.0
* TDA 6 EO	7.0
* TDA 7 EO	6.0
Water-1	15.0
Water-2	20.0
Acetic acid	0.2-0.3
Water-3	35.0
Butyl di-glycol	1-2% (co-surfactant, if necessary)

* TDA: tridecyl alcohol ethoxylate

Method:

-
- Take Ecofluid-8417 & surfactants in a SS vessel and stir for 20-25 mins.
 - Add water-1 gradually under constant stirring and stir for 30 mins.
 - Add water-2 and stir for 20 mins.
 - Add water-3 and acetic acid; mix and stir for further 10-15 mins.
 - Add 1-2% co-surfactant if necessary.
 - Testing.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone: +91 22 42184218

Fax: +91 22 42184350

Email: tcmtkg@sarex.com

URL: www.sarex.com

PRODUCT LITERATURE

ECOFLUID - 8417

should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 8 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PE127 | Last Upd. On : 25/06/15] [MOLL]

This is a computer generated report. Hence not signed.