



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone: +91 22 42184218

Fax : +91 22 42184350

Email : [tcmtkg@sarex.com](mailto:tcmtkg@sarex.com)

URL : [www.sarex.com](http://www.sarex.com)

## PRODUCT LITERATURE

### ECOGUARD-SR 6

#### Product Information

Ecoguard-SR 6 is a new generation stain releasing fluorocarbon based on C6 chemistry. It imparts very good stain release properties on cotton, polyester and their blends. It also imparts oil and water repellency. The finish on substrate allow the stains to leave fabric faster and makes the fabric clean. Treated fabric is durable to multiple home launderings.

#### Key Features & Benefits

Key Features -----	Benefits -----
Performance	Excellent stain release coupled with oil and water repellency
Ecofriendly	PFOA below detectable limit
Durable	Good stain release property even after multiple home laundering
Feel	Does not impair breathability and handle of the fabric
Non-yellowing	Suitable for white and pastel shades

#### General Characteristics

Physical appearance	: Off white liquid
Ionic nature	: Nonionic to weakly cationic
pH of 1% solution	: 5 +/-1
Miscibility	: Miscible with water
Compatibility	: Compatible with cationic, anionic and nonionic products
Stability	: Stable to dilute acids and dilute alkalies

#### Application

Pick-up	: 65-70%
Bath pH	: 4.5-5.0
Drying	: 110-130 deg.C



**Sarex Chemicals**

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone: +91 22 42184218

Fax : +91 22 42184350

Email : [tcmtkg@sarex.com](mailto:tcmtkg@sarex.com)

URL : [www.sarex.com](http://www.sarex.com)

## PRODUCT LITERATURE

### ECOGUARD-SR 6

Curing : 160-170 deg.C, 2-3 min.

#### SUGGESTED RECIPES:

-----  
1. 100% Cotton

Ecoguard-SR 6	:	30-50*g/l
Saralink-ULF	:	30 g/l (optional)
MgCl <sub>2</sub> **	:	6 g/l
Saralube-2975	:	20 g/l (optional)
IPA	:	5 g/l
Crosslink-SC (Conc)	:	5-8 g/l
Acetic acid	:	1-2 g/l

2. Polyester/Cellulosic blend

Ecoguard-SR 6	:	20-40*g/l
Saralink-ULF	:	20 g/l (optional)
MgCl <sub>2</sub> **	:	4 g/l
Saralube-2975	:	20 g/l (optional)
IPA	:	5 g/l
Crosslink-SC (Conc)	:	3-4 g/l
Acetic acid	:	1-2 g/l

3. 100% Polyester

Ecoguard-SR 6	:	20-40*g/l
Saralube-2975	:	20 g/l (optional)
IPA	:	4 g/l
Crosslink-SC (Conc)	:	3-4 g/l
Acetic acid	:	1-2 g/l

\* Concentration of Ecoguard-SR 6 to be taken on the basis of durability requirement.

\*\* If Saralink-ULF is added in the recipe then only MgCl<sub>2</sub> to be added.

#### Note:

- 1. It is recommended to prewash the substrate to be treated with 1 g/l Saragen-DAM at 80-85 deg.C for 20-30 min. to remove



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone: +91 22 42184218

Fax : +91 22 42184350

Email : [tcmlktg@sarex.com](mailto:tcmlktg@sarex.com)

URL : [www.sarex.com](http://www.sarex.com)

## PRODUCT LITERATURE

### ECOGUARD-SR 6

traces of residual impurities to get excellent results.

2. Crosslink-SC(Conc) is an extender, addition of which improves fastness to washing and resistance to abrasion.

Sequence of addition:

- Prepare bath with all ingredients including Saralink-ULF MgCl<sub>2</sub> and Crosslink-SC(Conc) in water containing Acetic acid.
- Stir continuously and add Ecoguard-SR 6 as the final ingredient.

Precautions:

- Avoid high speed and continuous stirring.
- Avoid silicone based softeners in the finishing recipe.

#### Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 8 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]  
[ Prod.Code :PE227 | Last Upd. On : 07/10/15 ] [PP]

This is a computer generated report. Hence not signed.