



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

KAYNOL-LSA

Product Information

Kaynol-LSA is a medium foaming, solvent free, APEO free wetting cum detergent for all type of fibres to remove stubborn oil, grease or wax dirt. Kaynol-LSA can be used in batch as well as in continuous process. The product is also suitable for high temperature scouring and bleaching of cotton, lycra and their blends. Kaynol-LSA gives an excellent cleaning performance for fabrics blended with lycra. Kaynol-LSA is also used to clean raw wool.

Key Features & Benefits

Key Features

Medium to low foaming wetting agent and detergent

Powerful emulsifying

Stable at high temperature

Benefits

Suitable for soft flow and jet dyeing machines

Removal of silicone oils from lycra and synthetic fabrics.

Suitable for high temperature scouring, bleaching and high temperature combined scouring and bleaching.

General Characteristics

Physical Appearance : Colourless clear viscous liquid
Ionic Nature : Non-ionic
pH of 1% solution : 6 +/- 1
Miscibility : Easily miscible with water.
Stability : Stable to dilute acids & dilute alkalies
Compatibility : Compatible with cationic, anionic and non-ionic products.

Application

Cotton and cotton lycra
For combined scouring and bleaching :

0.7-1% : Kaynol-LSA
2-3% : Caustic soda flakes
3-8% : H2O2 50%



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

KAYNOL-LSA

0.5-1% : Saraquest-2UD (optional)
0.3-1.2%: Sarastabil-MRS
Treat at 98 deg.C for 45-90 min. or 110 deg.C for 15-45 min.
MLR 1:10

Synthetic fibres.

0.70-1% : Kaynol-LSA

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 8 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PK042 | Last Upd. On : 27/02/17] [MOLL]

This is a computer generated report. Hence not signed.