



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

## PRODUCT LITERATURE

### KETOPREP-LA

#### Product Information

Ketoprep-LA is a novel, all in one pretreatment product. It is a biodegradable product and require low alkali during bleaching of cellulosic substrate. Bleaching with Ketoprep-LA exhibits very good softness, absorbency, rewetting and whiteness than the conventional bleached fabric. Bleached fabrics confers low strength loss and weight loss as concentration of alkali used in bleaching is low. Yarn bleached with Ketoprep-LA decreases the coefficient of friction, improves strength and reduces harshness to a certain extent.

#### Key Features & Benefits

##### Key Features

-----  
Low alkali short time bleaching

Eco-friendly

##### Benefits

-----  
- High degree of whiteness and low strength loss  
- Saves time, water and energy

- Low BOD/COD and TDS in effluent bath  
- Readily biodegradable

#### General Characteristics

Physical appearance : Light Blue liquid

Ionic nature : Anionic

pH of 1% solution : 6 +/-1

Miscibility : Misible with water

Compatibility : Compatible with anionic and nonionic products

Stability : Stable to dilute acids and dilute alkalies

#### Application

##### 1. Recipe for RFD (Ready for dyeing) (Atmospheric bleaching)

-----  
Ketoprep-LA : 0.8-1.0%  
Caustic flakes : 1.5-1.75%  
Hydrogen Peroxide (50% v/v) : 2-2.5%  
Temperature : 95-98 deg.C, 30-45 min.

##### 2. Recipe for full white (Atmospheric bleaching)



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218

Fax +91 22 42184350

Email : tcmktg@sarex.com

URL www.sarex.com

## PRODUCT LITERATURE

### KETOPREP-LA

-----

Saraquest-W (Conc) : 0.1% (Optional)  
 Ketoprep-LA : 1.2-1.5%  
 Caustic flakes : 2-2.5%  
 Hydrogen Peroxide (50% v/v) : 6.0-8.0%  
 Temperature : 95-98 deg.C, 60 min.

To achieve better whiteness index, optical brightening agent (OBA) to be added in hot wash

#### 3. Recipe for high temperature bleaching (110 deg.C)

-----

	Ready for Dyeing	Full White
	-----	-----
Ketoprep-LA	: 0.8-1.0%	1.2-1.5%
Caustic flakes	: 1-1.25%	1.25-1.75%
Hydrogen peroxide (50% v/v)	: 1-1.25%	5-6%
Temperature	: 110 deg.C	110 deg.C
Time	: 15-20 min.	30-40 min.

### Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 8 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]  
[ Prod.Code :PK051 | Last Upd. On : 15/11/17 ] [MOLL]

This is a computer generated report. Hence not signed.