



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARASOL-1101

Product Information

Sarasol-1101 is a thickening agent which is applied in the pre-treatment padding process before Ink-Jet printing on various substrates. Sarasol-1101 is suitable on all types of fabrics printed with disperse, reative and acid inks. Sarasol-1101 being a high molecular weight product locally increases the viscosity thereby prevents spreading of prints. Sarasol-1101 delivers level prints with sharp outlines and improved colour value. It has a film forming and adhesion property. The advantage of Sarasol-1101 is ready to use product with consistent viscosity. Sarasol-1101 is stable as there is no bacterial attack. The feel of the fabric is not affected.

Key Features & Benefits

Key Features	Benefits
-----	-----
Ink Jet printing	Improves colour yield, levelness & sharpness of prints on cotton, polyester, wool, silk and polyamide fabrics
Universal	Suitable for all types of ink
Easy wash-off	Does not interfere in subsequent processing

General Characteristics

Physical appearance	: Colourless clear viscous liquid
Ionic nature	: Anionic
pH of 1% solution	: 7 +/-1
Miscibility	: Miscible with water
Compatibility	: Compatible with anionic and nonionic products
Stability	: Stable to dilute acids and dilute alkalies

Application

1. Ink-Jet printing on Polyester (Disperse ink)

Pre-treatment (Padding)

Sarasol-1101	: 50-80 g/l
Sarakol-NF	: 1-3 g/l



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARASOL-1101

Kitex-BO : 5-10 g/l

Pad -> Dry -> Print (Ink-jet printing)

Ink-Jet Printing

Printing : Ink-jet with disperse ink
Steaming : 170-180 deg.C, 6-8 min. OR
Thermofix : 180-190 deg.C, 1-2 min. OR
Calendering : 200-210 deg.C, 30 sec.

After-treatment (washing)

Cold wash : 5 mins.
Reduction clearing: 0.5-0.75 g/l, Reducon-ACD (Conc) at
4.5-5.0 pH, 60-70 deg.C, 10 mins.

2. Ink-Jet printing on Cotton or Viscose (Reactive ink)

Pre-treatment

Sarasol-1101 : 60-100 g/l
Sarakol-NF : 1-3 g/l
Urea : 50-100 g/l
Soda ash : 30-40 g/l
Super R Salt : 10-15 g/l

Pad -> Dry -> Print (Ink-Jet printing)

Ink-Jet Printing

Printing : Ink-Jet with Reactive ink
Steaming : 102-105 deg.C, 7-10 min. OR
Thermofix : 140-150 deg.C, 3-5 min.

After treatment (Washing)

Cold wash : 5 mins
Soaping : 1-2 g/l Sarakol-1583, 98 deg.C, 5 mins. (twice)
Hot wash : 3 mins at boil (twice)
Cold wash : 5 mins.



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218

Fax +91 22 42184350

Email : tcmktg@sarex.com

URL www.sarex.com

PRODUCT LITERATURE

SARASOL-1101

3. Ink-Jet printing on Silk, Wool, Polyamide (Acid ink)

Pre-treatment

Sarasol-1101	:	60-80	g/l
Sarakol-NF	:	1-3	g/l
Urea	:	80-100	g/l
Ammonium sulphate (25%)	:	10-20	g/l
Supergen-MX	:	10	g/l

Pad -> Dry -> Print (Ink-Jet printing)

Ink-Jet Printing

Printing	:	Ink-Jet with Acid ink
Steaming	:	102-105 deg.C, 30-40 mins.followed by washing

Incase of Polyamide / Wool, fixation with 1-3% Sarafix-(NEW), pH 4.5-5.5 at 70-80 deg.C for 15-20 min is recommended.

Note:

- Sarasol-1101 can be applied by coating with 50% diluted product.
- Concentration of Sarasol-1101 to be added depending on GSM of fabric. For higher GSM fabric, lesser quantity of Sarasol-1101 is required compared to lower GSM fabric.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 8 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PY647 | Last Upd. On : 13/12/16] [PP]

This is a computer generated report. Hence not signed.