



# Sarex Chemicals

(A Divn. of Saraf Chemicals Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri (W), Mumbai-400 058. INDIA

Phone (91-22) 4218 4218 Fax (91-22) 4218 4350

Email : tcmktg@sarex.com URL www.sarex.com

## PRODUCT LITERATURE

### SARAPRINT-AC

#### Product Information

Saraprint-AC is a melamine formaldehyde based resin used for finishing of interlining fabrics to impart a durable stiff handle. It is particularly effective for prints taken on knitted, cellulosic fabrics, polyester/cotton, polyester/viscose and polyamides. Addition of Saraprint-AC to a pigment paste enhances its fastness properties especially scrub fastness and wet rubbing fastness.

It is also used for imparting stiff handle to polyester fabrics and its blends.

#### Key Features & Benefits

##### Key Features

-----

Cross-linking polymer

Higher dosage gives stiff finish.

##### Benefits

-----

Improvement in dry, wet and scrub rub fastness of pigment prints

Finishing of cotton inter-lining.

#### General Characteristics

Physical appearance : Colourless viscous liquid  
Ionic nature : Nonionic  
pH of 1% solution : 7 +/- 1  
Miscibility : Readily miscible with water  
Compatibility : Compatible with anionic, cationic and nonionic products  
Stability : Stable to dilute acids & dilute alkalies

#### Application

1. In pigment printing:

1-3% Saraprint-AC can be added in paste made from either kerosin emulsion or synthetic polymers.

2. Finishing of cotton, polyester, polyamide and their blends



# Sarex Chemicals

(A Divn. of Saraf Chemicals Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri (W), Mumbai-400 058. INDIA

Phone (91-22) 4218 4218 Fax (91-22) 4218 4350

Email : tcmktg@sarex.com URL www.sarex.com

## PRODUCT LITERATURE

### SARAPRINT-AC

10-30 g/l Saraprint-AC  
pH 5-6, pick up 60-70% by pad-dry-cure method.

#### Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]  
[ Prod.Code :PS736 | Last Upd. On : 16/08/2010 ] [SJ]

This is a computer generated report. Hence not signed.