



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218

Fax +91 22 42184350

Email : tcmktg@sarex.com

URL www.sarex.com

PRODUCT LITERATURE

SARALINK-ULF

Product Information

Saralink-ULF is low temperature curing and ultra low formaldehyde cross linking agent for cotton and polyester / cellulosic blends to impart durable press finish with very low free formaldehyde. It can also apply at high temperature. It meets Oekotex requirement. With Saralink-ULF, DP rating of 3.5 can be obtained depending on recipe and process. Saralink-ULF is also suitable for DP finishing of garments by spraying or soaking technique.

Key Features & Benefits

Key Features

Ultra low formaldehyde

Efficient cross linking

Benefits

Suitable for outerwear to meet Oekotex requirement

DP rating 3+ can be obtained depending on the recipe

General Characteristics

Physical appearance : Colourless to pale yellow clear liquid

Ionic nature : Nonionic

pH of 1% solution : 4 +/- 1

Miscibility : Miscible with water

Compatibility : Compatible with cationic, anionic and nonionic products

Stability : Stable to dilute acids and dilute alkalies

Application

I. PADDING PROCESS (Durable press finish)

=====

Pick-up : 65-70 %

Bath pH : 5.0-6.0

Low temp.curing : 125-135 deg.C, 4-5 mins.

High temp.curing : 150-160 deg.C, 3-4 mins.

Shock curing : 170-180 deg.C, 30-45 sec.

Suggested Recipe

1. 100% Cotton Shirting & Cotton B/W



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218

Fax +91 22 42184350

Email : tcmktg@sarex.com

URL www.sarex.com

PRODUCT LITERATURE

SARALINK-ULF

Saralink-ULF : 60-120 g/l
MgCl₂ : 12-25 g/l
Citric acid : 0.3 g/l
Megatouch : 5-15 g/l
Macrosoft-W : 5-15 g/l
Saralube-2975 : 20-30 g/l

2. Polyester / Cellulosic blends

Saralink-ULF : 40-60 g/l
MgCl₂ : 8-12 g/l
Citric acid : 0.3 g/l
Sarasoft-1371 : 10-15 g/l
Macrosoft-W : 10-15 g/l
Saralube-2975 : 10-20 g/l

II. EXHAUST PROCESS

=====

Bath pH : 4.5-5.0
Bath Temp. : Room temperature
Time : 10-30 mins.
Hydroextract, Tumble dry
Drying : 125-160 deg.C, 3-5 mins.

Suggested Recipe

1. Wrinkle free treatment of garments

Saralink-ULF : 6-12 %
Saralube-2975 : 2-3 %
Garfinish-GRU : 1-2 %
MgCl₂ : 1.2-2.4 %
Citric acid : 0.3 %
Sarawet-NF : 1-2 g/l

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 8 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PS156 | Last Upd. On : 16/11/16] [MOLL]



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARALINK-ULF

This is a computer generated report. Hence not signed.