



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARAPEACH-MR

Product Information

Sarapeach-MR is a self-crosslinking polymeric finish which imparts softness as well as fullness to the finished fabric. Sarapeach-MR is a new softener introduced to give peach skin effect to fabrics without emerising. Sarapeach-MR can be used on all fabrics and garments made from natural as well as synthetic fibres for durable, soft and peach skin effect.

Key Features & Benefits

Key Features

Good softness with drape

Durable

Benefits

Special finishes for high value cotton shirting & polyester dress material

Fast to domestic laundering

General Characteristics

Physical appearance : Colourless to pale yellow liquid
Ionic nature : Nonionic
pH of 1.0% solution : 5 +/- 1
Miscibility : Miscible with water
Compatibility : Compatible with anionic, cationic and nonionic finishing agents.
Pre-trials are required for cationic products
Stability : Stable to dilute acids and dilute alkalies

Application

Padding Process:

Dosage : 10-40 g/l
Pick-up : 65-70%
Bath pH : 5.0-6.0
Drying : 130-160 deg.C, 2-3 mins.
Shock curing : 170-180 deg.C, 30-45 secs.

Exhaust Process (Garment m/c):



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218

Fax +91 22 42184350

Email : tcmktg@sarex.com

URL www.sarex.com

PRODUCT LITERATURE

SARAPEACH-MR

Dosage : 6-25 g/kg
Bath pH : 5.0-6.0
Bath Temp. : 30-40 deg.C, 10-15 mins.
Hydroextract, Tumble dry
Drying & curing : 130-160 deg.C

Note:

Sarapeach-MR can be applied by spraying or by exhaust method followed by hydroextraction, tumble drying and curing along with resin. Best results are obtained by spraying method.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 8 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PS788 | Last Upd. On : 05/02/16] [MOLL]

This is a computer generated report. Hence not signed.