



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-LTH

Product Information

Careguard-LTH is a new generation fluorocarbon based on C6 Chemistry. It can be applied by padding foam and by spray technique. Careguard-LTH gives very high water repellency on synthetics such as Acrylic, Polyester, etc. It passes Bundesmann test.

Key Features & Benefits

Key Features	Benefits
-----	-----
Durable	Good water repellency after multiple home laundering
No Roller build-up and no gumming	Suitable for high speed finishing operations
Non ionic	- No tailing during pad application

General Characteristics

Physical appearance	: Off white liquid
Ionic nature	: Nonionic
pH of 1% solution	: 5 +/- 1
Miscibility	: Miscible with water
Compatibility	: Compatible with anionic, cationic and nonionic products
Stability	: Stable to dilute acids and dilute alkalies

Application

Pick-up	: 65-70%
Bath pH	: 4.0 - 4.5
Drying	: 100 - 120 deg.C
Curing	: 150 deg.C,5 min. OR 160 deg.C,3 min. OR 170 deg.C, 1 min.

SUGGESTED RECIPES:

For all substrates

Careguard-LTH : 20-80 g/l



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-LTH

Acetic Acid : 0.5 g/l
IPA : 5 g/l

* Concentration of Careguard-LTH to be taken on the basis of durability requirement.

* For extended durability, addition of Crosslink-SC(Conc) is recommended

Note:

1. It is recommended to prewash the substrate to be treated with 1 g/l Saragen-DAM at 80-85 deg.C for 20-30 min. to remove traces of residual impurities to get excellent results.
2. After padding and drying if fabric is kept overnight before curing, results will be further improved.
3. Compatible with Flame Retardent finish (Pre-trial is recommended).
4. Water-oil repellent finish can be combined with resin finish using 30g/l Saralink-ULF + 6g/l MgCl₂ + 20g/l Saralube-2975.

Sequence of addition:

- Prepare bath with all ingredients including Saralink-ULF, MgCl₂ in water containing Acetic acid.
- Stir continuously and add Careguard-LTH as the final ingredient.

Precautions:

- Avoid high speed and continuous stirring.
- Avoid silicone based softeners in the finishing recipe.
- Pre trial with Careguard-LTH is recommended with coating chemicals.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-LTH

Shelf Life : 8 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PC596 | Last Upd. On : 15/02/19] [MOLL]

This is a computer generated report. Hence not signed.