



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218

Fax +91 22 42184350

Email : tcmktg@sarex.com

URL www.sarex.com

PRODUCT LITERATURE

ESTOFEEL (CONC)

Product Information

Estofeel (Conc) is specially developed hydrophilic finishing agent for polyester, polyamide and other synthetic fibres to overcome the generated static charge. It also improves wicking property of cellulosic fibres. Estofeel (Conc) imparts hydrophilicity, antistatic, soil release and soil resistant properties to hydrophobic fibres. On cellulose and its blends Estofeel (Conc) imparts soil release property against corn oil, coffee, ketchup and chocolate stains.

Key Features & Benefits

Key Features

Antistatic and hydrophilic

Concentrated

Dyeing

Durable

Versatile

Cost effective

Soil release and soil resistant

Benefits

Comfort properties for polyester and polyester rich blends

Economical

Compatible with dyeing recipe by exhaust process

Durable to home laundering

Applicable by padding as well as by exhaust method

Price advantage to customer

Value added finish

General Characteristics

Physical appearance : Yellow pellets to irregular lumps

Ionic nature : Nonionic

pH of 1% solution : 5 +/- 2

Miscibility : Miscible with hot water

Compatibility : Compatible with cationic, anionic and nonionic products

Stability : Stable to dilute acids and dilute alkalies



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

ESTOFEEL (CONC)

Application

Padding process

Dosage : 5-8 g/l (10%)
Pick-up : 65-70 %
Bath pH : 5.5-6.0
Drying : 120 deg.C, 2 mins.
Curing : 170 deg.C, 1 min. (Polyester)
 : 160 deg.C, 1 min. (Polyamide)

Exhaust process

Dosage : 0.5-0.8% (10%)
Bath pH : 5.5-6.0
Bath Temp. : 130 deg.C
Time : 30-45 mins.

Instructions For Dilution

[I] Procedure to prepare 10% Estofeel (Conc)

- Take 90 parts of DM water of 60-70deg.C
- To this, gradually add Estofeel (Conc) with constant stirring using paddle stirrer (50-100 rpm)
- Continue stirring at 60-70 deg.C for 60-90 mins. to get homogenous product
- Lower down the temperature to 40 deg.C under constant stirring
- Filter/Strain the finished product to remove un-dissolved particles/lumps if any.

Note:

- pH of the diluted product should be 6-7
- Temperature of DM water should not go beyond 70 deg.C

[II] Procedure to prepare 17% Estofeel (Conc)

- Melt 173 parts of Estofeel (Conc)
- To this, add 825 parts of water under stirring
- To this, gradually add 7.5 parts of NaOH (33%), 38 Bc under stirring
- Add preservative and continue stirring for 30-45 min to obtain homogenous solution
- Filter/Strain to remove un-dissolved particles/lumps if any.
- pH of 17% Estofeel (Conc) will be 8+/-1

Preservation: It is recommended to add 0.1% Bronopol (2-Bromo,2-nitropropane, 1,3-diol) or Methyl Paraben (methyl



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email : tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

ESTOFEEL (CONC)

para hydroxy benzoate) as an antimicrobial agent to avoid fungal/microbial growth.

Estofeel (Conc) is not freeze thaw stable.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PE225 | Last Upd. On : 28/05/19] [MOLL]

This is a computer generated report. Hence not signed.