

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W), Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email: tcmktg@sarex.com **URL** www.sarex.com

# PRODUCT LITERATURE

## UNIV-AIO

#### Product Information

Univ-AIO is a very low foaming speciality product for pretreatment of cotton yarn, cotton knits, terry towels and their blends available in powder form. Due to it's unique formulation it acts as a wetting agent, detergent and peroxide stabiliser and also no caustic is required during bleaching. Thus, combined scouring and bleaching can be carried out using only peroxide alongwith Univ-AIO. As caustic is not added during bleaching the total dissolved solids (TDS) of effluent will be low.

Due to low foaming characteristic, it is suitable for soft flow machines as well as low liquor ratio package dyeing machines and jet dyeing machines.

### Key Features & Benefits

Benefits Key Features \_\_\_\_\_

Wetting agent, detergent and peroxide Unique formulation

stabiliser

process

No caustic used in the Lower degradation and weight loss of

treated fabric

Stable at high Combined scouring and bleaching can be carried out at high temperature temperature

Low foaming Suitable for soft flow and jet

dyeing machines

\_ Low Chemical Oxygen Demand (COD) Eco-friendly

of effluent

- Low total dissolved solids (TDS) in

effluent

#### General Characteristics

Physical appearance : Off White to White granules

Ionic nature : Anionic pH of 1% solution : 13 +/- 1

Miscibility : Soluble in water

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W), Mumbai 400 058. INDIA

Email:tcmktg@sarex.com URL www.sarex.com

# PRODUCT LITERATURE

## UNIV-AIO

Compatibility : Compatible with anionic and

nonionic products

Stability : Stable to dilute alkalies and

unstable to dilute acids

### **Application**

For Soft flow machine :

1. Recipe for RFD fabric (Ready for Dyeing fabric) :

Univ-AIO : 1.5-2.0 %

Hydrogen peroxide (50%) : 2-2.5 %

Temperature : 95-110 deg.C

Time : 45-15 min

2. Recipe for Full white fabric:

Univ-AIO : 2.5-3.5 % Hydrogen peroxide (50%) : 6.0-8.0 % Temperature : 95-110 deg.C Time : 75-30 min

Note: For high GSM fabric, 0.1 % Saracrease-HG (Conc) is

recommended.

### Instructions For Dilution

Univ-AIO to be used as is

### Precautions

Storage : Store in cool, ventilated shed away from

heat and direct sunlight. Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if

stored under controlled conditions.

[The above information is given in good faith and is without warranty] [Prod.Code :PU015 | Last Upd. On : 04/05/18 ] [MOLL]

This is a computer generated report. Hence not signed.