



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-903

Product Information

Careguard-903 is a new generation water and oil repelling fluorocarbon based on C6 Chemistry. It imparts durable water and oil repelling effects on various substrates viz., polyester, cotton, nylon, wool fibres and their blends. It can be applied by padding foam and by spray technique. Careguard-903 gives very high water repellency on synthetics such as Acrylic, Polyester, etc. It passes Bundesmann test.

Key Features & Benefits

Key Features

Durable

No Roller build-up
and no gumming

Non ionic

Benefits

Good water/oil repellency after multiple
home laundering

Suitable for high speed finishing
operations

- No tailing during pad application
- Compatible with various softeners

General Characteristics

Physical appearance : White to off white liquid
Ionic nature : Nonionic
pH of 1% solution : 6 +/- 1
Miscibility : Miscible with water
Compatibility : Compatible with anionic, cationic and
nonionic products
Stability : Stable to dilute acids and dilute alkalies

Application

Pick-up : 65-70%
Bath pH : 4.0 - 4.5
Drying : 100 - 120 deg.C
Curing : 150 deg.C, 5 min. OR 160 deg.C, 3 min. OR
170 deg.C, 1 min.

SUGGESTED RECIPES:



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-903

For all substrates

Careguard-903 : 20-80 g/l
Acetic Acid : 0.5 g/l
IPA : 5 g/l

* Concentration of Careguard-903 to be taken on the basis of durability requirement.

* For extended durability, addition of Crosslink-SC(Conc) is recommended

Note:

-
1. It is recommended to prewash the substrate to be treated with 1 g/l Saragen-DAM at 80-85 deg.C for 20-30 min. to remove traces of residual impurities to get excellent results.
 2. After padding and drying if fabric is kept overnight before curing, results will be further improved.
 3. Compatible with Flame Retardent finish (Pre-trial is recommended).
 4. Water-oil repellent finish can be combined with resin finish using 30g/l Saralink-ULF + 6g/l MgCl₂ + 20g/l Saralube-2975.

Sequence of addition:

-
- Prepare bath with all ingredients including Saralink-ULF, MgCl₂ in water containing Acetic acid.
 - Stir continuously and add Careguard-903 as the final ingredient.

Precautions:

-
- Avoid high speed and continuous stirring.
 - Avoid silicone based softeners in the finishing recipe.
 - Pre trial with Careguard-903 is recommended with coating chemicals.

Precautions

Storage : Store in cool, ventilated shed away from



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-903

heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PC591 | Last Upd. On : 23/11/18] [PP]

This is a computer generated report. Hence not signed.