



**Sarex Overseas**

(A Divn. Of Saraf Chemicals Ltd.)

502 Waterford C Wing, C.D.Bariwala Marg(Juhu Lane), Andheri (W), Mumbai-400 058. INDIA

**Phone:** (91-22) 4218 4218

**Fax :** (91-22) 4218 4350

**Email :** sales@sarex.com

**URL :** www.sarex.com

## PRODUCT LITERATURE

### EVERSOFT-152

#### Product Information

Eversoft-152 is a new generation nonionic micro silicone softener specially developed to impart soft, silky handle for all types of woven & knitted fabric. The particle size of Eversoft-152 is designed such a way that, it penetrates softness into the fabric to give luxurious soft handle. Eversoft-152 has also elastomeric property coupled with softness. Eversoft-152 is applied by exhaust as well as by padding.

#### Key Features & Benefits

##### Key features

-----

Extra ordinary softness

Durable

Elastomeric

##### Benefits

-----

Extremely soft silky handle

Fast to several home launderings

Improves strength and elastomeric property specially to knits

#### General Characteristics

Physical appearance : Colourless to pale yellow liquid  
Ionic nature : Nonionic  
pH of 1% solution : 6 +/- 2  
Miscibility : Miscible with water  
Compatibility : Compatible with anionic, cationic & nonionic products  
Stability : Stable to dilute acids and stable to dilute alkalies

#### Application

##### 1. Pad application

10-30 g/l Eversoft-152, depending on requirements

pH 5-6 adjusted with acetic acid, pick up 65-70%, dry at 140-160 deg.C.

##### 2. Exhaust application for garments.



**Sarex Overseas**

(A Divn. Of Saraf Chemicals Ltd.)

502 Waterford C Wing, C.D.Bariwala Marg(Juhu Lane), Andheri (W), Mumbai-400 058. INDIA

**Phone:** (91-22) 4218 4218

**Fax :** (91-22) 4218 4350

**Email :** sales@sarex.com

**URL :** www.sarex.com

## PRODUCT LITERATURE

### EVERSOFT-152

1-3% Eversoft-152 (o.w.f.)

pH 5-6 adjusted with acetic acid, treat at 35-40 deg c. for 20-30 min.

#### **Precautions**

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.