



Sarex Overseas

(A Divn. Of Saraf Chemicals Ltd.)

502 Waterford C Wing, C.D.Bariwala Marg(Juhu Lane), Andheri (W), Mumbai-400 058. INDIA

Phone: (91-22) 4218 4218

Fax: (91-22) 4218 4350

Email : sales@sarex.com

URL : www.sarex.com

PRODUCT LITERATURE

SARADET-2485

Product Information

Saradet-2485 is a low foaming, solvent free APEO/NPEO detergent and scouring agent with good wetting action for scouring of cotton, yarn, knits, terry towels, fabric and cotton blends. Due to its low foaming characteristics, the product is suitable for jet dyeing machine even at low liquor ratio. The product is also suitable for high temperature scouring and combined scouring and bleaching at boil as well as at high temperature.

Key Features & Benefits

Key Features

Low foaming Wetting agent
dyeing machines

Powerful emulsifying
action

Stable to high temperature

Benefits

Suitable for soft flow and jet and detergent

Excellent removal of fat, waxes and
oils thereby ensuring uniform
absorbency

Suitable for high temperature
scouring, bleaching and high
temperature combined scouring and
bleaching.

General Characteristics

Physical Appearance : Straw White Gel

Ionic Nature : Non-ionic

pH of 1% solution : 8 +/- 2

Miscibility : Easily miscible with water.

Stability : Stable to dilute acids, dilute alkalies
and hard water commonly encountered in
textile processing.

Compatibility : Compatible with cationic, anionic and
non-ionic products.

Application

1. For scouring and combined scouring and bleaching :



Sarex Overseas

(A Divn. Of Saraf Chemicals Ltd.)

502 Waterford C Wing, C.D.Bariwala Marg(Juhu Lane), Andheri (W), Mumbai-400 058. INDIA

Phone: (91-22) 4218 4218

Fax : (91-22) 4218 4350

Email : sales@sarex.com

URL : www.sarex.com

PRODUCT LITERATURE

SARADET-2485

0.5-1.5% : Saradet-2485
2-4% : Caustic soda flakes
3-8% : H2O2 50%
0.5-1% : Saraquest 2UD
0.3-1.2% : Sarastabil MRS
Treat at 98 deg.C for 40-90 min. OR 110 deg.C for 15-45 min.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.