



Sarex Overseas

(A Divn. Of Saraf Chemicals Ltd.)

502 Waterford C Wing, C.D.Bariwala Marg(Juhu Lane), Andheri (W), Mumbai-400 058. INDIA

Phone: (91-22) 4218 4218

Fax : (91-22) 4218 4350

Email : sales@sarex.com

URL : www.sarex.com

PRODUCT LITERATURE

SARACLEAN-M

Product Information

Saraclean-M is a low foaming, solvent free wetting cum detergent for scouring of cotton yarn, knits, terry towels, fabric and cotton blends. Due to its low foaming characteristics, the product is suitable for jet dyeing machine even at low liquor ratio. The product is also suitable for high temperature scouring and combined scouring and bleaching at boil as well as at high temperature.

Key Features & Benefits

Key Features

Low foaming and detergent

Powerful emulsifying action

Stable to high temperature

Benefits

Suitable for soft flow and jet dyeing machines

Excellent removal of fat, waxes and oils thereby ensuring uniform absorbency

Suitable for high temperature scouring, bleaching and high temperature combined scouring and bleaching.

General Characteristics

Physical Appearance : Straw white gel

Ionic Nature : Non-ionic

pH of 1% solution : 7.5+/-1

Miscibility : Easily miscible with water.

Stability : Stable to dilute acids, dilute alkalies and hard water commonly encountered in textile processing.

Compatibility : Compatible with cationic, anionic and non-ionic products.

Application

1. For combined scouring and bleaching :



Sarex Overseas

(A Divn. Of Saraf Chemicals Ltd.)

502 Waterford C Wing, C.D.Bariwala Marg(Juhu Lane), Andheri (W), Mumbai-400 058. INDIA

Phone: (91-22) 4218 4218

Fax : (91-22) 4218 4350

Email : sales@sarex.com

URL : www.sarex.com

PRODUCT LITERATURE

SARACLEAN-M

0.7-1.5% : Saraclean-M
2-3% : Caustic flakes
3-8% : H2O2 50%
0.5-1% : Saraquest 2UD
0.3-1.2% : Sarastabil MRS
Treat at 98 deg.C for 40-90 min. OR 110 deg.C for 15-45 min.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.