

# Sarex Overseas (A division of Sarex Organics Pvt. Ltd.)

Corporate Office: 501-502, Waterford, C Wing, Juhu Lane, Andheri (W), Mumbai - 400 058, India. Phone: +91(22) 6128 5566 / 4218 4218, Fax: +91(22) 4218 4350.

Web: www.sarex.com • Email: fchem@sarex.com



## **Technical data Sheet**

# SARAFAST UVT

**UV Absorber for Technical Textile** 

### **Product Information**

- Sarafast UVT is Triazine based dispersion, suitable for High Temperature Exhaust Application, printing and continuous pad-thermosol application.
- It is suitable for Dyeing and printing of polyester Fibres, modified polyester Fibres and their blends that are exposed to critical light and heat conditions.
- Sarafast UVT provide outstanding stability against heat and light.

## **Key Features & Benefits**

Key Features	Benefits
UV absorber	Reduces fibre damage
Triazine chemistry:Triazine chemistry is undeniably a cornerstone of modern industrial advancements, known for best UV stability.	Counteracts photochemical Fibre and dye degradation, especially on long-term exposure to light and heat
Outstandingly stable to heat and light.	Safe fulfillment of light fastness requirements even after post-setting and molding processes.  Fast to sublimation, no tendency to fogging.
Highest extinction rates over a wide range of UV rays.	Full absorption of UV rays hence maximum light fastness, functionality and stability of PES Fibres
Highly Exhaustible	In exhaust dyeing processes, the product is completely picked up by the polyester material and builds-up to a high level of UV absorption - thus showing a high efficiency in reduce colour fading.
Stable to alkaline conditions.	Suitable for dyeing in alkaline conditions as well as alkaline discharge printing processes.
Low viscosity and good storage stability.	Pumpable and easy to handle. Suitable for container transport and storage.
Fine particle size with remarkable dispersion stability properties.	Homogeneous dispersion, even at a high heating rate and under unfavorable dyeing conditions like package dyeing.
Good dispersion stability and low foaming	Suitable by exhaust method in soft flow, package & jet dying machine

Products currently covered by valid US patents are offered for R&D use in accordance with 35 USC 271 (e) (I) Above information is given in good faith and without warrenty.



# Sarex Overseas (A division of Sarex Organics Pvt. Ltd.)

**Corporate Office:** 501-502, Waterford, C Wing, Juhu Lane, Andheri (W), Mumbai - 400 058, India. **Phone:** +91(22) 6128 5566 / 4218 4218, **Fax:** +91(22) 4218 4350.

Web: www.sarex.com • Email: fchem@sarex.com



## **Technical data Sheet**

## SARAFAST UVT

**UV Absorber for Technical Textile** 

### **General Characteristics**

Physical appearance : White to pale yellow dispersion

Chemical Constitution : Dispresant- containing Triazine derivative

Ionic nature: Non-ionicpH of 1% solution: 6.5-8Specific Gravity at 20°C:  $1.05 \text{ g/cm}^3$ 

Miscibility : Dispersible with water

Compatibility : Compatible with anionic and non-ionic products

Stability : Stable in hard water to acids and alkalies, pH values 4 to 10

## **Application**

Sarafast UVT UV absorber is added to the liquor at the start of the dyeing cycle and applied by the HT exhaust or pad-thermosol method.

Stir well before removal from the container

- 1. Exhaust application during polyester dyeing with disperse dyes.
- Dosage : 2-6%(on weight of the fabric)
- 2. Thermosol pad application
- Dosage: 15-50 g/l(50-60% liquor pick-up)

#### Note

- Sarafast UVT can be applied in presence of carrier, however the carrier residues may impair the light fastness properties of fabric.
- The effects attainable depend on the type of polyester Fibre (texture, amount of delustrant, denier and cross section), the dyes used and the individual shade.
- Sarafast UVT shows a slightly yellow self-shade in printing and pad-thermosol application. Certain bright shades might be impaired by this whereas on trichromatic systems it could minimize the fading of the yellow component.

#### **Precautions**

Storage: Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should

not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

**Shelf Life:** 9 months from the date of manufacturing, if stored under controlled conditions.

Packing: 50 kg, 200 kg HDPE Drum

Disclaimer