



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-6NI

Product Information

Careguard-6NI is a new generation cost effective water and oil repelling fluorocarbon based on C6 Chemistry. It imparts durable water and oil repelling effects on various substrates viz., polyester, cotton, nylon, wool fibres and their blends. It can be applied by padding foam and by spray technique.

Key Features & Benefits

Key Features -----	Benefits -----
Competitive	Better water and oil repellency than the conventional C6 fluorocarbons
Durable	Good water and oil repellency after multiple home laundering
Versatile	Applicable on all substrates

General Characteristics

Physical appearance	: Off white liquid
Ionic nature	: Nonionic to weakly cationic
pH of 1% solution	: 5 +/- 1
Miscibility	: Miscible with water
Compatibility	: Compatible with cationic and nonionic products
Stability	: Stable to dilute acids and dilute alkalies

Application

Pick-up	: 65-70%
Bath pH	: 4.0 - 4.5
Drying	: 100 - 120 deg.C
Curing	: 150 deg.C, 5 min. OR 160 deg.C, 3 min. OR 170 deg.C, 1 min.

SUGGESTED RECIPES:

For all substrates



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-6NI

Careguard-6NI : 20-80 g/l
Acetic Acid : 0.5 g/l
IPA : 5 g/l

* Concentration of Careguard-6NI to be taken on the basis of durability requirement.

* For extended durability, addition of Crosslink-SC(Conc) is recommended

Note:

-
1. It is recommended to prewash the substrate to be treated with 1 g/l Saragen-DAM at 80-85 deg.C for 20-30 min. to remove traces of residual impurities to get excellent results.
 2. After padding and drying if fabric is kept overnight before curing, results will be further improved.
 3. Compatible with Flame Retardent finish (Pre-trial is recommended).
 4. Water-oil repellent finish can be combined with resin finish using 30g/l Saralink-ULF + 6g/l MgCl₂ + 20g/l Saralube-2975.

Sequence of addition:

-
- Prepare bath with all ingredients including Saralink-ULF, MgCl₂ in water containing Acetic acid.
 - Stir continuously and add Careguard-6NI as the final ingredient.

Precautions:

-
- Avoid high speed and continuous stirring.
 - Avoid silicone based softeners in the finishing recipe.
 - Pre trial with Careguard-6NI is recommended with coating chemicals.



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CAREGUARD-6NI

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PC503 | Last Upd. On : 15/03/18] [PP]

This is a computer generated report. Hence not signed.