



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARASOFT-I (CONC)

Product Information

Sarasoft-I (Conc) is a specially developed softener for cotton, polyester, wool and their blends. It imparts soft and limpy handle to treated substrate. Sarasoft-I (Conc) can be applied by pad as well as by exhaust application. Thus it is suitable to finish the fabric in any form such as yarns, knits, wovens or even garments.

It does not impair the whiteness or brightness of garments.

Key Features & Benefits

Key Features -----	Benefits -----
Non-yellowing	Suitable for finishing of whites & pale shades
Universal softener	Single product for finishing cotton, polyester, wool and their blends and garments
Versatile	Suitable for padding and exhaust in soft flow / jet dyeing machine

General Characteristics

Physical appearance	: Creamish viscous liquid / paste
Ionic nature	: Cationic
pH of 1% solution	: 5 +/- 2
Miscibility	: Miscible with water
Compatibility	: Compatible with cationic and nonionic products
Stability	: Stable to dilute acids and unstable to dilute alkalies

Application

Exhaust process :

Cotton Yarns / Garments



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARASOFT-I (CONC)

Dosage : 1-2%
Bath pH : 5.0-6.0
Temp : 30-40 deg.C
Time : 20-30 mins.

Padding process :

Dosage : 5-10 g/l
Sarasoft-EP : 20-30 g/l (Optional)
Pick-up : 65-70%
Bath pH : 5.0-6.0
Drying : 130-160 deg.C

Note :

-
1. Before finishing, fabric should be rinsed thoroughly to remove traces of detergents, alkali, salt used in earlier process. This improves the performance of Sarasoft-I (Conc)
 2. Sarasoft-I (Conc) not to be used with pigment printed fabrics or with any finish which is anionic in nature.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :PS704 | Last Upd. On : 10/10/14] [PP]

This is a computer generated report. Hence not signed.