



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARASOL-1101

Product Information

Sarasol-1101 is a thickening agent which is applied in the pre-treatment padding process before Ink-Jet printing on various substrates. Sarasol-1101 is suitable on all types of fabrics printed with disperse, reactive and acid inks. Sarasol-1101 being a high molecular weight product locally increases the viscosity thereby prevents spreading of prints. Sarasol-1101 delivers level prints with sharp outlines and improved colour value. It has a film forming and adhesion property. The advantage of Sarasol-1101 is ready to use product with consistent viscosity. Sarasol-1101 is stable as there is no bacterial attack. The feel of the fabric is not affected.

Key Features & Benefits

Key Features	Benefits
-----	-----
Ink Jet printing	Improves colour yield, levelness & sharpness of prints on cotton, polyester, wool, silk and polyamide fabrics
Universal	Suitable for all types of ink
Easy wash-off	Does not interfere in subsequent processing

General Characteristics

Physical appearance	: Colourless clear viscous liquid
Ionic nature	: Anionic
pH of 1% solution	: 6+/-1
Miscibility	: Miscible with water
Compatibility	: Compatible with anionic and nonionic products
Stability	: Stable to dilute acids and dilute alkalies

Application

1. Ink-Jet printing on Polyester (Disperse ink)

Pre-treatment (Padding)

Sarasol-1101 : 50-80 g/l

Sarakol-NF : 1-3 g/l



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARASOL-1101

Kitex-BO : 5-10 g/l

Pad -> Dry -> Print (Ink-jet printing)

Ink-Jet Printing

Printing : Ink-jet with disperse ink
Steaming : 170-180 deg.C, 6-8 min. OR
Thermofix : 180-190 deg.C, 1-2 min. OR
Calendering : 200-210 deg.C, 30 sec.

After-treatment (washing)

Cold wash : 5 mins.
Reduction clearing: 0.5-0.75 g/l, Reducon-ACD (Conc) at
4.5-5.0 pH, 60-70 deg.C, 10 mins.

2. Ink-Jet printing on Cotton or Viscose (Reactive ink)

Pre-treatment

Sarasol-1101 : 60-100 g/l
Sarakol-NF : 1-3 g/l
Urea : 50-100 g/l
Soda ash : 30-40 g/l
Super R Salt : 10-15 g/l

Pad -> Dry -> Print (Ink-Jet printing)

Ink-Jet Printing

Printing : Ink-Jet with Reactive ink
Steaming : 102-105 deg.C, 7-10 min. OR
Thermofix : 140-150 deg.C, 3-5 min.

After treatment (Washing)

Cold wash : 5 mins
Soaping : 1-2 g/l Sarakol-1583, 98 deg.C, 5 mins. (twice)
Hot wash : 3 mins at boil (twice)
Cold wash : 5 mins.



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARASOL-1101

3. Ink-Jet printing on Silk, Wool, Polyamide (Acid ink)

Pre-treatment

Sarasol-1101	:	60-80	g/l
Sarakol-NF	:	1-3	g/l
Urea	:	80-100	g/l
Ammonium sulphate (25%)	:	10-20	g/l
Supergen-MX	:	10	g/l

Pad -> Dry -> Print (Ink-Jet printing)

Ink-Jet Printing

Printing	:	Ink-Jet with Acid ink
Steaming	:	102-105 deg.C, 30-40 mins. followed by washing

Incase of Polyamide / Wool, fixation with 1-3% Sarafix-(NEW), pH 4.5-5.5 at 70-80 deg.C for 15-20 min is recommended.

Note:

- Sarasol-1101 can be applied by coating with 50% diluted product.
- Concentration of Sarasol-1101 to be added depending on GSM of fabric. For higher GSM fabric, lesser quantity of Sarasol-1101

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :L008783 | Last Upd. On : 14/10/19 [MOLL]

This is a computer generated report. Hence not signed.