



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Bariwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

FLAMGUARD-DPS.

Product Information

Flamguard-DPS. is durable flame retardant finishing chemical for 100% polyester and polyester rich blend. Flamguard-DPS. is halogen free. Fabric finished with Flamguard-DPS. shows minimum effect on shade and posses good fastness to home laundering and dry cleaning. Flamguard-DPS. does not have any effect on the drape of the treated fabric. Flamguard-DPS. has low volatility and does not lead to fogging. Flamguard-DPS. is suitable for protective work wear, furnishing fabrics, curtains and automotive textiles made from 100% polyester and polyester rich blend. It is applicable by padding and by spray method. They can be applied on polyester and polypropylene nonwoven fabrics also.

Key Features & Benefits

Key Features	Benefits
-----	-----
Durable	Durable to home laundering and dry cleaning
Feel	Handle of fabric not impaired

General Characteristics

Physical appearance	: Clear to translucent viscous liquid
Ionic nature	: Nonionic
pH of 1% solution	: 4 +/-1
Miscibility	: Miscible with water
Compatibility	: Compatible with cationic, anionic and nonionic products
Stability	: Stable to dilute acids and dilute alkalies

Application

Before finishing with Flamguard-DPS., ensure that residues from earlier treatment such as lubricants, surfactants, softeners, dyeing chemicals etc. are thoroughly removed by efficient washing otherwise these could interfere with performance of Flamguard-DPS.

Flamguard-DPS.	: 60-160 g/l
Sarawet NF	: 1-2 g/l (optional)
Pick-up	: 40-70%



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

FLAMGUARD-DPS.

Drying : 120-130 deg.C for 2 min
Thermofix : 160-170 deg.C, 3 min. or 190-210 deg.C, 30-60 sec.

- Ensure that the padding temperature does not exceed 30 deg.C
- The add-on with Flamguard-DPS. should be 14-15%

Flamguard-DPS. can pass following tests.

-
1. BS-3119 (1959) & BS-3120 Vertical flame test for flame proof materials
 2. BS-5867 & DOC FF 3/71

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :L009515 | Last Upd. On : 28/11/19] [MOLL]

This is a computer generated report. Hence not signed.