



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARAFINISH-SS

Product Information

Sarafinish-SS is a wash fast finishing agent for all types of fibres in any form i.e knits, wovens or garments. Finishing with Sarafinish-SS gives crisp dry handle to the treated material. Sarafinish-SS also improves resistance to pilling and gives anti-snap finish.

By using Sarafinish-SS, seam slippage tendencies are reduced. Sarafinish-SS can be applied by exhaust as well as pad application. The product can be applied in combination with water-repellent agents and with resins. Finish obtained with Sarafinish-SS is basically resistant to washing & dry cleaning.

Key Features & Benefits

Key Features

Universal

Versatile

Multifunction

Compatibility

Benefits

Suitable for all natural, synthetic fibres and blends

Can be applied by exhaust and pad

Anti-pilling, Anti-slip, Anti-snap finish can be developed

Can be used with resins as well as fluorochemicals

General Characteristics

Physical appearance : Straw white to milky white liquid
Ionic nature : Cationic
pH of 1% solution : 5 +/- 1
Miscibility : Miscible with water
Compatibility : Compatible with cationic & nonionic products, water repellent agents, softeners and resins
Stability : Stable to hard water and dilute acids.
Not stable to alkalies, phosphates and excess sulphates.



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARAFINISH-SS

Application

1. Exhaust Application:

Depending on the end use requirements,

0.5-4% of Sarafinish-SS

pH 5, treat at 35-40 deg.C for 20-40 min.

2. Pad Application:

5-20 g/l Sarafinish-SS

Pad at pH-5, 60-70% pick-up, dry/cure as per the normal finishing conditions.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :L008352 | Last Upd. On : 09/05/2020] [MOLL]

This is a computer generated report. Hence not signed.