



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmtkg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

ECOGUARD-SYN (CONC)

Product Information

Ecoguard-SYN (Conc) is a fluorine free speciality product for water repellency and rainproofing. Ecoguard-SYN (Conc) gives best results on synthetic fabrics and outer wear fabrics. The performance of Ecoguard-SYN (Conc) is very close to C6 fluoro chemicals in terms of water repellency and durability. It imparts sewability and also provides better resistance to abrasion and tear.

Key Features & Benefits

Key features

Benefits

Non-yellowing

Suitable for white and pastel shades

Fluorine free

Fulfills requirement of leading retailers viz. M&S and H&M

Performance

Works very well on synthetics and outer wear fabrics

Close to C6 fluorocarbon in terms of water repellency and durability

Durable

Withstands multiple home laundering

General Characteristics

Physical appearance : Off white liquid
Ionic nature : Nonionic to weakly cationic
pH of 1% solution : 5 +/- 1
Miscibility : Miscible with water
Compatibility : Compatible with cationic and nonionic products
Stability : Stable to dilute acids and dilute alkalies

Application

Padding Process:

Ecoguard-SYN (Conc) : 30-100 g/l



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

ECOGUARD-SYN (CONC)

Pick-up : 65-70%
Bath pH : 6.0-7.0
Drying : 120 deg.C, 2 min.
Curing* : 145-150 deg.C, 3 min. OR 170 deg.C
for 40 sec.

* In case of polyester, at maximum pick up, curing at temperature 145-150 deg.C gives better spray rating.

* In case of polyester and P/W fabric it is recommended to wash fabric with 0.5-1 g/l Saragen-DAM before finishing.

Exhaust process for Garment/fabrics

Ecoguard-SYN (Conc) : 4-10%
Bath pH : 6.0 - 7.0
Bath Temp. : R.T. to 40 deg.C, (1 deg.C/min.)
Time : 30-40 min. at 40 deg.C
Drying/Curing : 110 deg.C, 3 min. / 145-150 deg.C, 3 min.
OR 170 deg.C for 40 sec.

Note:

- Filtration of Ecoguard-SYN (Conc) after stirring and before diluting is recommended.

It is recommended to prewash the substrate with 1 g/l Saragen-DAM at 80-85 deg.C for 20-30 min to remove traces of residual impurities to get excellent results

Preliminary trials are recommended before bulk processing

- For higher durability 5-10 g/l of Ecolink (Conc) can be used
- To get very good results with Ecoguard-SYN (Conc) pick up should be more than 70%
- The minimum 145 deg.C temperature for curing is recommended



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

ECOGUARD-SYN (CONC)

get better results

- Ecoguard-SYN (Conc) is suitable with Deca based FR products but it is not to be used with phosphorous based and APP (Ammonium Phosphophate) based FR products
- Before finishing with Ecoguard-SYN (Conc), bring the fabric temperature to room temperature
- The impairment of the repellent effects will occur by adding analogous auxillaries into the finishing bath.

To avoid impairment of the repellent effect mechanical treatment such as calendering, brushing etc. to be avoided

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :L004604 | Last Upd. On : 18/05/20] [PP]

This is a computer generated report. Hence not signed.