



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

ECOLINK (CONC)

Product Information

Ecolink (Conc) is an ecofriendly crosslinking agent for water-oil repellent finishing agent. Addition of Ecolink (Conc) improves durability to multiple home launderings.

Key Features & Benefits

Key Features	Benefits
Improves crosslinking	Improves durability of finished fabric
Eco friendly	Free from Butane oxime and Meko free
Feel	Original hand of fabric is not affected

General Characteristics

Physical appearance	: Off white liquid
Ionic nature	: Nonionic
pH of 1% solution	: 8 +/- 1
Miscibility	: Miscible with water
Compatibility	: Compatible with cationic, anionic and nonionic products
Stability	: Stable to dilute acids and dilute alkalies

Application

Pick-up	: 65-70%
Bath pH	: 4.5 - 5.5
Drying	: 110 deg.C
Curing	: 160-170 deg.C, 2-3 min.

SUGGESTED RECIPES:

* Careguard (Conc)	: 50-70 g/l - 100% Cotton fabric
* Caregaurd (Conc)	: 30-40 g/l - P/C & P/V
Ecolink (Conc)	: 2-4 g/l
IPA	: 5 g/l

* Any water-oil repellent finishing agent.



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

ECOLINK (CONC)

Sequence of addition:

- Stir continuously and add Ecolink (Conc) as the final ingredient.

Note:

-
1. It is recommended to prewash the substrate to be treated with 1 g/l Saragen-DAM at 80-85 deg.C for 20-30 min. to remove traces of residual impurities to get excellent results.
 2. After padding and drying if fabric is kept overnight before curing, results will be further improved.
 3. Avoid silicone based softeners in the finishing recipe.
 4. Check the compatability of other finishing chemicals in finish formulation.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code : L009717.docx | Last Upd. On : 25/05/20] [PP]

This is a computer generated report. Hence not signed.