



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane),
Ancheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email :tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARASOL-763

Product Information

Sarasol-763 is a high viscosity thickening agent which is applied in pre-treatment process of Ink-Jet printing. Sarasol-763 gives sharp and even prints with improved colour values especially on viscose and cellulosic substrates. It also delivers even and sharp prints on the substrates printed with disperse and acid dyes. Sarasol-763 does not affect the original hand of fabric. The quality of final print obtained with Sarasol-763 is much better than that obtained with conventional thickeners.

Key Features & Benefits

Key Features	Benefits
Ink Jet printing	- Sharp and even prints - Improvement in colour value
High quality print	- Better than the conventional thickeners - Suitable for black and dark shades
Easy wash-off	Does not interfere in subsequent processing

General Characteristics

Physical appearance	: Colourless viscous liquid
Ionic nature	: Anionic
pH of 1% solution	: 10 +/-1
Miscibility	: Miscible with water
Compatibility	: Compatible with anionic and nonionic products
Stability	: Stable to dilute acids and dilute alkalies

Application

1. Ink-Jet printing on Viscose and cotton (Reactive ink)

Pre-treatment

Sarasol-763	: 40-60 g/l (Cotton)
	: 60-80 g/l (Viscose)
Sarakol-NF	: 1-5 g/l
Urea	: 50-100 g/l



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane),
Anheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 **Fax** +91 22 42184350

Email :tcmktg@sarex.com **URL** www.sarex.com

PRODUCT LITERATURE

SARASOL-763

Soda ash : 30-40 g/l
Super R Salt : 10-20 g/l

Pad -> Dry -> Print (Ink-Jet printing)

Ink-Jet Printing

Printing : Ink-Jet with Reactive ink
Steaming : 102-105 deg.C, 7-10 min.

After treatment (Washing)

Cold wash : 5 mins.
Soaping : 1 g/l Sarakol-CR, 98 deg.C, 5 mins.(twice)
Hot wash : 3 mins at boil (twice)
Cold wash : 5 mins.

2. Ink-Jet printing on Polyester (Disperse ink)

Pre-treatment (Padding)

Sarasol-763 : 60-80 g/l
Sarakol-NF : 1-5 g/l

Pad -> Dry -> Print (Ink-Jet printing)

Ink-Jet Printing

Printing : Ink-jet with disperse ink
Steaming : 170-180 deg.C, 8 min.
Calendering : 200-210 deg.C, 30 sec.

After-treatment (washing)

Cold wash : 5 mins.
Soaping : 1 g/l Sarakol-CR at 40 deg.C, 5 mins.
Reduction clearing: 0.75-1 g/l, Reducon-ACD (Conc) at
4.5-5.0 pH, 60-70 deg.C, 10 mins.



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane),
Ancheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email :tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARASOL-763

3. Ink-Jet printing on Silk, Wool, Polyamide (Acid ink)

Pre-treatment

Sarasol-763	:	60-80	g/l
Sarakol-NF	:	3-8	g/l
Urea	:	80-100	g/l
Ammonium sulphate (25%)	:	10-20	g/l
Supergen-MX	:	10	g/l

Pad -> Dry -> Print (Ink-Jet printing)

Ink-Jet Printing

Printing	:	Ink-Jet with Acid ink
Steaming	:	102-105 deg.C, 10-20 mins.followed by washing

Incase of Polyamide / Wool, fixation with 0.4-1.5 g/l Sarafix (NEW), pH 4.5-5.5 at 70-80 deg.C for 15-20 min is recommended.

Note:

1. Sarasol-763 can be applied by coating with 50% diluted product.
2. Concentration of Sarakol-NF to be added depending on GSM of fabric. For lower GSM fabric, lesser quantity of Sarakol-NF is required compared to higher GSM fabric.

Precautions

Storage	:	Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.
Shelf Life	:	9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :L009251 | Last Upd. On : 27/05/2020] [MOLL]

This is a computer generated report. Hence not signed.