

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W), Mumbai 400 058. INDIA

Email tcmktg@sarex.com URL www.sarex.com

# PRODUCT LITERATURE

## **YUVI-493**

### Product Information

Yuvi-493 is a UV absorber for Polyester. It reduces the fibre damage due to photo chemical degradation. Yuvi-493 has very good dispersion stability and is therefore particularly suitable in exhaust method of application. Yuvi-493 has no influence on the shade of dyeings.

## Key Features & Benefits

Key Features Benefits

UV absorber Reduces fibre damage

Good dispersion stability Suitable by exhaust method in soft flow,

and low foaming package & jet machine's during dyeing

#### General Characteristics

Physical appearance : Greenish yellow liquid

Ionic Nature : Anionic
pH of 1% solution : 7 +/- 1

Miscibility : Dispersible with water

Compatibility : Compatible with anionic and non-ionic products

Stability : Stable to dilute acids and dilute alkalies

## **Application**

1. Exhaust application during polyester dyeing with disperse dyes.

Dosage : 2-4%

2. Thermosol pad application
 Dosage : 10-30 g/1

### Note:

\_\_\_\_

- Yuvi-493 can be applied in presence of carrier, however the carrier residues may impair the light fastness properties of fabric.



501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Email tcmktg@sarex.com URL www.sarex.com

## PRODUCT LITERATURE

## **YUVI-493**

- Yuvi-493 sublimates at higher thermosoling temperatures. Pre-lab trials are recommended. Sublimation can be compensated by increasing the dosage of Yuvi-493.

### **Precautions**

Storage : Store in cool, ventilated shed away from

heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if

stored under controlled conditions.

[The above information is given in good faith and is without warranty] [ Prod.Code :L008956 | Last Upd. On : 18/08/2020 ] [PP]

This is a computer generated report. Hence not signed.