



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

## PRODUCT LITERATURE

### SARAKOL-NF

#### Product Information

Sarakol-NF is a low foaming wetting and deaerating agent for continuous dyeing as well as exhaust application, particularly for dyeing of yarn packages. Due to its excellent wetting action, proper wetting takes place in short time particularly in continuous dyeing which results into uniform shade. In exhaust application it helps to remove entrapped air thus leading to thorough wetting before addition of any other chemical. Sarakol-NF can also be added in desizing by pad batch application to improve pick-up. Sarakol-NF is stable in high concentration of caustic.

#### Key Features & Benefits

##### Key Features

Low foaming

Wetting & penetrating

Deaerating

##### Benefits

Colour specks due to foam eliminated

Uniform dye pick-up in padding

Uniform dyeing in continuous dyeing operation

#### General Characteristics

Physical appearance : Colourless to pale yellow clear liquid  
Ionic nature : Anionic  
pH of 1% solution : 7 +/-1  
Miscibility : Miscible in water  
Compatibility : Compatible with anionic & nonionic products  
Stability : Stable to dilute acids & dilute alkalies (stable in 40-50 g/l caustic)

#### Application

##### 1. Exhaust-application

1-2 g/l Sarakol-NF

Add at room temperature and circulate for 5 mins. before addition of any other chemicals.



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email [tcmtkg@sarex.com](mailto:tcmtkg@sarex.com) URL [www.sarex.com](http://www.sarex.com)

## PRODUCT LITERATURE

### SARAKOL-NF

2. Pad-application

2-5 g/l Sarakol-NF

#### Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]  
[ Prod.Code : L006836.docx | Last Upd. On : 24/08/20 ] [PP]

This is a computer generated report. Hence not signed.