

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W), Mumbai 400 058. INDIA

Email:tcmktg@sarex.com URL www.sarex.com

# PRODUCT LITERATURE

## DELTASOFT-CLC

#### Product Information

Deltasoft-CLC is a new generation polysiloxane softener. It is suitable for all types of fabrics viz., Polyester, Cotton and blends. No dryness or roughness in finished fabric is observed during storage. It gives very good results on polyester/viscose blends. It imparts body break on the treated fabrics. Deltasoft-CLC is suitable by pad and by exhaust application as it is shear stable is suitable in yarn package dyeing machine and soft flow (jet) machine.

#### Key Features & Benefits

Key Features Benefits \_\_\_\_\_

Soft finish No dryness or roughnes observed during storage

Applied by padding and by exhaust in garment Versatile

drum machine

#### General Characteristics

Physical appearance: Colourless to light yellow, transparent to slight hazy liquid

Ionic nature : Nonionic pH of 1% solution : 5 + /- 1

Miscibility

: Miscible with water
: Compatible with cationic, anionic and nonionic products Compatibility

: Stable to dilute acids and dilute alkalies Stability

## Application

Padding process Exhaust process \_\_\_\_\_ \_\_\_\_\_\_

Dosage : 20-60 g/l Dosage : 2-6% Pick-up : 65-70% Bath pH : 5.0-6.0 Bath pH : 5.0-6.0 Bath Temp.: 30-40 deg.C Drying : 130-160 deg.C Time : 20-30 mins.



501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

**Email**:tcmktg@sarex.com **URL** www.sarex.com

# PRODUCT LITERATURE

# **DELTASOFT-CLC**

### **Precautions**

Storage : Store in cool, ventilated shed away from

heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if

stored under controlled conditions.

[The above information is given in good faith and is without warranty] [ Prod.Code :L009811 | Last Upd. On : 18/08/20 ] [MOLL]

This is a computer generated report. Hence not signed.