



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

RUBFAST-716

Product Information

Rubfast-716 is a speciality finishing agent to improve dry and wet rub fastness of all types of dyed and printed cotton and their blends. It is suitable for indigo denim fabric as it will not give back staining and patchiness during finishing. Rubfast-716 can be applied by both dry-on-wet and wet-on-wet application.

Key Features & Benefits

Key Features

Excellent improvement in wet rub fastness by padding

No adverse effect

Benefits

Improves by 1.5-2.0 units on direct reactive, sulphur, indigo and pigment dyed fabrics

Does not affect the washing fastness and original handle of fabric

General Characteristics

Physical appearance : Light Yellow to brownish yellow viscous liquid
Ionic nature : Amphoteric
pH of 1% solution : 4 +/- 1
Miscibility : Miscible with water
Compatibility : Compatible with non-ionic products
Stability : Stable to dilute acids and dilute alkalies

Application

Padding method:

=====

Step wise procedure for preparing Rubfast-716 solution

- Take required quantity of Rubfast-716 (30 g/l)
- To this, gradually add water (pH 5.8-6.2) and make the total volume
- Mix well to get uniform solution



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

RUBFAST-716

- Solution of 30 g/l Rubfast-716 will appear Colourless to straw white liquid with pH 3.7-4.2

Padding Application:

Pad -> Dry at 130-160 deg.C

Exhaust method - in Garment:

=====

Step wise procedure for preparing Rubfast-716 solution

- Take required quantity of (3-5% on weight of garment) and mix it uniformly
- To this, gradually add water (pH 5.8-6.2) and make the total volume
- Mix well to get uniform solution
- Solution of 3-5% Rubfast-716 will appear Colourless to straw white liquid with pH 3.7-4.2

Exhaust process:

40deg.C, 20-30 min (with intermittent stirring)

Dry --> Curing @ 150-160 deg.C, 2-3 min

Note:

1. Fabric to be treated should be free from anionic components.
2. pH of the fabric should be neutral.
3. Absorbency of fabric should be instant. To improve absorbency of all over printed fabric (reactive/pigment), 0.2-0.5 g/l Celldet-R (wetting agent) is to be added in the finishing bath.
4. For garments, it is essential to cure at 150 deg.C after exhaustion
5. Rubfast-716 has limited durability to washing



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

RUBFAST-716

Special Instructions:

- If the water pH>6.2, adjust it to pH 5.8-6.2 and then use.
- 30 g/l Rubfast-716 will appear Colourless to straw white.
- Avoid using hard water.
- Prepare the solution at room temperature (approx.30 deg.C)
- The prepared solution to be kept under constant stirring and to be used immediately
- Do not keep Rubfast-716 stock solution standing.
- Ensure that the padding bath pH is 3.7-4.2 throughout the process.
- Pre-lab trials are recommended with other finishing agents.
- On standing the product tends to turn darker.

Precautions

Storage	: Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.
Shelf Life	: 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]

[Prod.Code L010173 | Last Upd. On : 09/03/2021] [PP]