



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CELLBIND-FF

Product Information

Cellbind-FF is an free formaldehyde binder for pigment printing of cellulosic and its blends. It gives very good brightness and soft and elastic handle feel to printed fabrics. It increases the resistance to abrasion. It imparts very good wash and rubbing fastness. Cellbind-FF can also be used as a coating agent to impart soft feel to the fabric.

Key Features & Benefits

Key Features	Benefits
-----	-----
Feel of the fabric handle	Soft and elastic handle

General Characteristics

Physical appearance	: Off white liquid
Ionic nature	: Anionic
pH of 1% solution	: 8 +/- 1
Miscibility	: Miscible with water
Compatibility	: Compatible with anionic and nonionic products
Stability	: Stable to dilute acids and dilute alkalies

Application

* For pigment printing, it is very essential that the fabric should be acidic around pH 5.5 to 6.

* To get good sharp print, the fabric should be free of salts before printing.

Paste preparation

Take recommended quantity of Cellbind-FF. Add 20% water and pigment emulsion as per shade depth. Then add Urea with stirring. Then add slowly half the quantity of synthetic thickener so that paste becomes thick. Add liquor ammonia and fixer. Then add balance water with stirring. Finally add balance synthetic thickener till required viscosity is achieved. Stir it further 10 mins. to built viscosity and smoothness.

RECIPE FOR PIGMENT PRINTING



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CELLBIND-FF

For 100% Cotton (Woven or Knits)

=====

Pigment emulsion	upto 1%	above 1% upto 4%	above 4%
Cellbind-FF	8%	12%	3 times the pigment
Synthick P-328	1.5%	2%	2 to 2.5%
Urea	5%	5%	5%
Saraprint-AC	--	2%	2%
Liquor ammonia		1%	2%
Water	balance	balance	balance

Process :-

Print --> Dry in the drier at temp. above 130 deg.C --> Cure at 150 deg.C for 5 mins.

For PE/Cotton blend (Max. upto 67% PE)

=====

Pigment emulsion	upto 1%	above 1% upto 4%	above 4%
Cellbind-FF	8%	12%	3 times the pigment
Synthick P-328	1.5%	2%	2 to 2.5%
Urea	5%	5%	5%
Saraprint-AC	1%	2%	3%
Liquor ammonia	--	1%	2%
Water	balance	balance	balance

Process :-

Print --> Dry in the drier at temp. above 130 deg.C --> Cure at 150 deg.C for 5 mins.

For Coating

=====

Cellbind-FF : 50-70 parts
 Thickness : 2.4 parts
 Water : Remaining



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

CELLBIND-FF

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code : L010666.docx | Last Upd. On : 03/09/21] [PVR]

This is a computer generated report. Hence not signed.