



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218

Fax +91 22 42184350

Email : tcmktg@sarex.com

URL www.sarex.com

## PRODUCT LITERATURE

### FABCOAT-AR 100

#### Product Information

Fabcoat-AR 100 is an hard Acrylic coating agent, recommended as a coating compound for outdoor fabrics like sunscreens blinds. It is also used to impart body, dimensional stability to the fabric. It provides excellent UV and weather resistance.

#### Key Features & Benefits

Key Features

Benefits

-----

-----

Easy to coat

Forms clear and tack free films

#### General Characteristics

Physical appearance : Off white liquid

Ionic nature : Anionic

pH of 1% solution : 8 +/- 1

Miscibility : Miscible with water

Compatibility : Compatible with anionic and nonionic products

Stability : Stable to dilute acid and dilute alkalies

#### Application

- Pre-impregnation with flouorocarbon is recommended before coating
- Fabcoat-AR 100 can be applied by knife on air
- Coating is to be dried at 100-120 deg.C
- Curing should be done at 160 deg.C for 3 mins
- For achieving high add-on, Fabcoat-AR should be coated in 2 pass
- Addition of Fabcoat-AR 100 in the coating recipe can help in getting hard handle on the fabric



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218

Fax +91 22 42184350

Email : tcmktg@sarex.com

URL www.sarex.com

## PRODUCT LITERATURE

### FABCOAT-AR 100

#### Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]  
[ Prod.Code :PF159 | Last Upd. On : 17/06/19 ] [MOLL]

This is a computer generated report. Hence not signed.