

501 Waterford, C Wing, C.D.Barfiwala Marg (Juhu Lane), Andheri(W), Mumbai 400 058. INDIA

**Phone -** +91 22 42184218 **Fax** +91 22 42184350 Email tcmktg@sarex.com URL www.sarex.com

# PRODUCT LITERATURE KATAFIX-HV

## Product Information

Katafix-HV is an all in one dye fixing agent for cellulosic's dyed with Reactive, Direct, Indigo and Sulphur dyestuffs. It shows very good improvement in colour fastness to washing. For Indigo denims, can be applied after desizing and before or after stone washing or enzyme treatment. Katafix-HV can be applied by exhaust as well as pad application.

## Key Features & Benefits

Benefits Key Features

Formaldehyde free Suitable for Oekotex and baby wear

Versatile Suitable for all anionic dyes

Improve wash fastness Works very well on Reactive, Indigo and Sulphur dyed Denim

fabric

## General Characteristics

Physical appearance: Colourless Clear Viscous Liquid

Ionic nature : Cationic pH of 1% solution : 6 +/- 1

Miscibility : Miscible with water

: Compatible with cationic and non-ionic products Compatibility : Stable to dilute acids and dilute alkalies Stability

# Application

# Exhaust Process (For Reactive dyed fabrics)

After thorough soaping of reactive dyed fabrics, treat in a fresh bath with below recipe:

Exhaust Process Continuous Process \_\_\_\_\_ \_\_\_\_\_

Dosage : 5-15 gpl
Pick-up : 65-70%
Bath pH : 5.0-5.5
Drying : 130-170 deg.C Dosage : 0.5-1.5% Bath pH : 5.0-5.5 Bath Temp : 30-40 deg.C

Time. : 15-30 min.

[The above information is given in good faith and is without warranty]

This is a computer generated report. Hence not signed.

Page: 1 of 2

Last Updated on: 10-07-2023 12:48

Document: L011275 Printed by: POOJA.V RAJAK



501 Waterford, C Wing, C.D.Barfiwala Marg (Juhu Lane), Andheri(W), Mumbai 400 058. INDIA

**Phone -** +91 22 42184218 **Fax** +91 22 42184350 Email tcmktg@sarex.com URL www.sarex.com

# PRODUCT LITERATURE KATAFIX-HV

#### Application (For Indigo & Sulphur dyed fabrics)

Exhaust Process Padding Process

Dosage :20-30 gpl
Pick-up :65-70%
Bath pH :5.0-5.5
Drying :110-130 deg.C Dosage : 2-3%
Bath pH : 5.0-5.5

Bath Temp : 30-40 deg.C Time. : 15-20 min.

Spray application: \_\_\_\_\_\_

Dosage : 20-30 gpl Bath pH : 5.0-5.5

\_\_\_\_\_

Spraying → Drying at 110-130 deg.C

#### Exhaust Process (For Direct dyed fabrics)

After thorough soaping of Direct dyed fabrics, treat in a fresh bath with below recipe:

\_\_\_\_\_\_

Exhaust Process

Dosage : 1.5-3%
Bath pH : 3.5-4.5 Dosage : 15-30 gpl
Pick-up : 65-70%
Bath pH : 3.5-4.5
Drying : 130-170 deg.C Bath Temp : 30-40 deg.C

Time. : 15-30 min.

### Precautions

Store in cool, ventilated shed away from heat and direct Storage

> sunlight. Storage temperature should not exceed 35 deg c. Close lids firmly to avoid contact with air and moisture.

Shelf Life 9 months from the date of manufacturing, if stored under

controlled conditions.

[The above information is given in good faith and is without warranty]

This is a computer generated report. Hence not signed.

Last Updated on: 10-07-2023 12:48

Page: 2 of 2

Document: L011275 Printed by: POOJA.V RAJAK