



PRODUCT LITERATURE

KATAFIX-BC

Product Information

Katafix-BC is an all in one dye fixing agent for cellulosic's dyed with Reactive, Direct, Indigo and Sulphur dyestuffs. It shows very good improvement in colour fastness to washing. For Indigo denims, can be applied after desizing and before or after stone washing or enzyme treatment. Katafix-BC can be applied by exhaust as well as pad application.

Key Features & Benefits

Key Features	Benefits
-----	-----
Formaldehyde free	Suitable for Oekotex and baby wear
Versatile	Suitable for all anionic dyes
Improve wash fastness	Works very well on Reactive, Indigo and Sulphur dyed Denim fabric

General Characteristics

Physical appearance: Colourless Clear Viscous Liquid
Ionic nature : Cationic
pH of 1% solution : 6 +/- 1
Miscibility : Miscible with water
Compatibility : Compatible with cationic and non-ionic products
Stability : Stable to dilute acids and dilute alkalies

Application

Exhaust Process (For Reactive dyed fabrics)

After thorough soaping of reactive dyed fabrics, treat in a fresh bath with below recipe:

Exhaust Process	Continuous Process
-----	-----
Dosage : 0.5-1.5%	Dosage : 5-15 gpl
Bath pH : 5.0-5.5	Pick-up : 65-70%
Bath Temp : 30-40 deg.C	Bath pH : 5.0-5.5
Time. : 15-30 min.	Drying : 130-170 deg.C



PRODUCT LITERATURE

KATAFIX-BC

Application (For Indigo & Sulphur dyed fabrics)

Exhaust Process

Dosage : 2-3%
Bath pH : 5.0-5.5
Bath Temp : 30-40 deg.C
Time. : 15-20 min.

Padding Process

Dosage : 20-30 gpl
Pick-up : 65-70%
Bath pH : 5.0-5.5
Drying : 110-130 deg.C

Spray application:

Dosage : 20-30 gpl
Bath pH : 5.0-5.5
Spraying → Drying at 110-130 deg.C

Exhaust Process (For Direct dyed fabrics)

After thorough soaping of Direct dyed fabrics, treat in a fresh bath with below recipe:

Exhaust Process

Dosage : 1.5-3% Dosage : 15-30 gpl
Bath pH : 3.5-4.5 Pick-up : 65-70%
Bath Temp : 30-40 deg.C Bath pH : 3.5-4.5
Time. : 15-30 min. Drying : 130-170 deg.C

Instructions for Dilutions :

Procedure to prepare 22% Katafix-BC

1. Take 50 parts of Katafix-BC
2. To this, gradually add 50 parts of DM water at 25-30°C under stirring
3. Continue stirring at 250-300 rpm for 15-20 min. using turbo stirrer to obtain homogenous solution

Precautions

Storage

Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg c. Close lids firmly to avoid contact with air and moisture.

Shelf Life

9 months from the date of manufacturing, if stored under controlled conditions.