



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

FABLUBE-F

Product Information

Fablube-F is amino silicone oil. Its emulsion imparts super soft, drapable and smooth handle to woven and knitted fabrics made up of cotton and cotton/polyester blends. Its emulsion can be applied by pad and exhaust application in garment drum washer.

Key Features & Benefits

Key Features

Cost effective

Good inner softness and drape

Benefits

Savings can be achieved

Incomparable touch

General Characteristics

Physical appearance	: Transparent to translucent viscous Liquid
Miscibility	: Immiscible with water
Viscosity (in cps at 25°C)	: 700-2000

Application

Recommended dosage of 20% emulsion

Padding process

Dosage : 15-40 g/l

Exhaust process for garments in drum washer

Dosage : 1.5-4%

Instructions For Dilution

Procedure to emulsify Fablube-F

It can be easily emulsified into stable micro emulsion using medium to high shear force stirrer.

Product	Parts
-----	-----
Fablube F	20.0
Tridecyl Alcohol ethoxylate 6.5 mole	9.0
Tridecyl Alcohol ethoxylate 9.0 mole	4.0



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

FABLUBE - F

Water (1st addition)	15.0
Acetic acid	0.2 - 0.3
Water (2nd addition)	20.0
Water (3rd addition)	31.8

- * First take Fablube F and surfactants (Tridecyl Alcohol ethoxylate 6.5 mole and Tridecyl Alcohol ethoxylate 9.0 mole and stir for 30-45 mins.
- * Add 15ml (Water 1st addition) and acetic acid mix gradually under constant stirring and stir for 30 min.
- * Add 20ml (Water 2nd addition) gradually and stir for 20 mins.
- * Add 31.8ml (Water 3rd addition) under constant stirring for 10-15 mins. till homogeneous product is formed.

Precautions

- Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.
- Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :L 011196.docx | Last Upd. On : 24 /02/24] [PVR]

This is a computer generated report. Hence not signed.