



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

RUBFAST-716

Product Information

Rubfast-716 is a speciality finishing agent to improve dry and wet rub fastness of all types of dyed and printed cotton and their blends. It is suitable for indigo denim fabric as it will not give back staining and patchiness during finishing. Rubfast-716 can be applied by both dry-on-wet and wet-on-wet application.

Key Features & Benefits

Key Features

Excellent improvement in wet rub fastness by padding

No adverse effect

Benefits

Improves by 1.5-2.0 units on direct reactive, sulphur, indigo and pigment dyed fabrics

Does not affect the washing fastness and original handle of fabric

General Characteristics

Physical appearance : Yellow to yellow brown liquid

Ionic nature : Amphoteric

pH of 1% solution : 4 +/- 1

Miscibility : Miscible with water

Compatibility : Compatible with nonionic products

Stability : Stable to dilute acids and unstable to dilute alkalies

Application

Step wise procedure for preparing Rubfast-716 solution

- Take required quantity of Rubfast-716 (30 g/l OR 3%)
- To this, gradually add water (pH 5.8-6.2) and make the total volume
- Mix well to get uniform solution
- Recipe of Rubfast-716 will appear Colourless to straw white liquid with pH 3.7-4.2. If this pH is not achieved, add 0.3-0.5gpl Acetic acid



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

RUBFAST-716

Padding Application:

Pad -> Dry at 130-160 deg.C

Exhaust process:

40deg.C, 20-30 min (with intermittent stirring)

Dry --> Curing @ 150-160 deg.C, 2-3 min

Special Instructions :

1. Fabric to be treated should be free from anionic components.
2. Absorbency of fabric should be instant.
3. For garments, it is essential to cure at 150 deg.C after exhaustion
4. If the water pH>6.2, adjust it to pH 5.8-6.2 and then use.
5. 30 g/l Rubfast-716 will appear Colourless to straw white.
6. Avoid using hard water.
7. Prepare the solution at room temperature (approx.30 deg.C)
8. Do not keep Rubfast-716 stock solution standing.
9. Ensure that the padding bath pH is 3.7-4.2 throughout the process.
10. Pre-lab trials are recommended with other finishing agents.
11. On standing the product tends to turn darker.
12. Rubfast-716 has limited durability to washings.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 12 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]

[Prod.Code L010173 | Last Upd. On : 05/07/2025] [PVR]